

## TECHNICAL SHEET 10.01.11-EN



# REVITALCOLOR

## Micro-reinforced acrylic façade paint

### 1. Description, Application

REVITALCOLOR is a micro-reinforced façade paint based on water dispersion of polymeric binders. It is suitable for decorative protection of all types of solid, embossed or rough and smoothed (fine rough), also repaired and, with regard to roughness, non-equalised façade surfaces (at least a month old lime-cement and cement render finishes, at least a month old unplastered concrete façade surfaces, fibre-cement and similar façade boards and similar). The paint film reinforced with thin synthetic fibres does not crack on spots of too-thick applications in furrows, channels and holes and it also fills well hair-cracks, i.e. cracks up to 0.3 mm wide. Application is also possible to well adhered old acrylic, silicate and silicone paint coats and decorative render finishes of all types.

Painted surfaces remain resistant to infection with the most widespread types of wall algae and mould for a long time, therefore Revitalcolor is also suitable for maintenance painting of façade surfaces infected with wall algae and mould if such surfaces are disinfected well prior to the application of the paint. The paint is distinguished by excellent coverage, good water vapour permeability and high water repellence. The paint film adheres to the surface well and is resistant to effects of smoke, ultraviolet radiation and other atmospheric factors; therefore, it is persistent in any climatic conditions including on façade surfaces of tall buildings, which are extremely exposed to precipitation and have minimum eaves.

### 2. Colour Shades

- white (colour shade 1001)
- shades under the colour chart JUB Home of Colours C-G, N, T, W with limitations - (on JUMIX tinting stations at points of sale!)
- shades under the colour chart JUB Favourite Feelings C-G - (on JUMIX tinting stations at points of sale!)
- tinting is also possible according to the NCS\* colour chart (on JUMIX tinting stations at points of sale)
- tinting is also possible according to the RAL CLASSIC\* colour chart (on JUMIX tinting stations at points of sale)
- delivery in colour shades designed at a special request of a customer is possible under certain conditions
- paints of various colour shades can be mixed in optional ratios!
- from now on, intensive colour shades are deliverable in colour shades of the façade paint Trendcolor

\* Due to certain limitations, number of colour shades can be lower than the total number of shades in colour

charts.

### 3. Technical data

|                                                             |                                                |                                            |                                                    |
|-------------------------------------------------------------|------------------------------------------------|--------------------------------------------|----------------------------------------------------|
| Packaging                                                   |                                                | 5 l, 15 l                                  |                                                    |
| Density                                                     |                                                | ~1.57 kg/dm³                               |                                                    |
| Content of vaporous substance (VOC)                         |                                                | 12 g/l                                     |                                                    |
| The EU VOC requirement - category                           |                                                | A/c<40                                     |                                                    |
| Water dilution mass                                         |                                                | 10%                                        |                                                    |
| Water dilution volume                                       |                                                | 15.7%                                      |                                                    |
| Drying time<br><br>T = +20 °C, relative air humidity = 65 % | Touch dry                                      | 3h                                         |                                                    |
|                                                             | Suitable for further treatment                 | 6h                                         |                                                    |
| Consumption                                                 |                                                | 300-700 ml/m² (for a two-coat application) |                                                    |
| Recommended number of layers                                |                                                | 2-3                                        |                                                    |
| Characteristics of a dry paint film                         | Vapor permeability EN ISO 7783-2               | μ, coefficient                             | <350                                               |
|                                                             |                                                | value Sd (d = 100 μm)                      | <0.04m<br>class 1 (high water vapour permeability) |
|                                                             | Water absorbtion w24 (EN 1062-3)               |                                            | <0.04kg/m2h0,5                                     |
|                                                             | Water absorbtion class                         |                                            | W3 - class 3 (Low)                                 |
|                                                             | Adhesion to conventional lime-cement (EN 1542) |                                            | >0.3MPa                                            |
|                                                             | Appearance                                     |                                            | matt                                               |

### 4. Installation Conditions

The temperature of the air and the wall base should be from +5 °C to +30 °C, and the relative air humidity should not be higher than 80%.

Protect façade surfaces against the sun, wind and rainfall with curtains; however, do not conduct any work in rain, fog or strong wind (≥30 km/h) despite such protection.

### 5. Surface Preparation

Surface should be solid, dry, and clean – without any badly-adhered particles, dust, remains of panelling oils, fat, or other dirt.

Drying time of new renders and levelling compounds in normal conditions (T = +20 °C, relative air humidity = 65 %) is at least 1 day for each mm of thickness, while for concrete surfaces the drying time is at least one month. From already painted surfaces, remove all paint coats, paints and precoat with oil paints, lacquers and enamels which get easily and quickly soaked in water. Surfaces infected with wall mould, must be disinfected prior to painting. In the event of potential repairs of façade surfaces that have been damaged in any way, follow only procedures, which assure, concerning roughness, as high a level of equalisation as possible to the repaired surface.

The application of primer is mandatory, both prior to first painting as well as prior to renovation painting. We recommend water-diluted JUKOL Primer (in ratio 1:1), water-diluted ACRYL Emulsion (in ratio 1:1), water-diluted SILICONE Primer (in ratio 1:1) or REVITALCOLOR paint diluted with water (in ratio 1:1) which are applied with a paintbrush or trowel, or with a long-bristled fur or textile paint roller (JUKOL Primer, ACRYL Emulsion and SILICONE Primer can also be applied by spraying).

If the surface is hair-cracked, cover it with REVITAL Primer once or twice. Before use, mix it well and, if necessary, dilute up to 5% with water. We apply it with a long-bristled fur or textile roller (the length of the bristles or threads is

18 to 20 mm; natural and artificial fur or textile covers made of various synthetic threads - polyamide, dralon, vestan, nylon, perlon or polyester) or with a roller brush suitable for applying dispersion coatings. Use a suitable draining screen when applying with a roller.

Painting can be started 6 hours after applying the primer under normal conditions ( $T = 20\text{ }^{\circ}\text{C}$ , relative humidity = 65%). For JUKOL Primer or REVITAL Primer, apply 12 hours after the base coat.

For technical information on these primers, please read the technical data sheet.

## 6. Preparation of Paint

Only stir the paint well prior to use and, if necessary, dilute it with water in accordance with consistency corresponding to application technique and conditions (see table above). ATTENTION! Paint coverage decreases with thinning!

We even out the color in a large enough container for the final wall surface (or even better: all surfaces on the object that we paint in the same shade). For large surfaces, when it is not technically possible to provide a sufficient amount of paint even for a single coat, mix the paint from at least three buckets in the leveling container. When we use up one-third of the prepared paint, we add new paint to the equalizing container and mix it well with the remaining paint in the container. It is not necessary to equalize the white color of the same production batch or the same production date that we have not diluted.

Any "correction" of the color during the painting process (adding tinting agents, thinning, etc.) is not allowed. We calculate or estimate the amount of paint needed to paint individual surfaces based on their surface area and average consumption data, and in specific cases, we determine consumption by measuring a sufficiently large test surface.

## 7. Paint Application

Apply the paint in two (exceptionally in three) coats using a long-bristle fur or textile paint roller (length of hairs or threads is 18 - 20 mm; the following can be used: natural and artificial fur or textile linings made of different synthetic threads – vestan, dralon, nylon, perlon or polyester) or a painting brush suitable for application of dispersion wall paints.

An individual wall surface is painted without interruptions from one end to the other. Always treat first the surfaces inaccessible to a standard long-bristle paint roller or to spraying gun (corners, gutters, narrow reveal surfaces, and similar) first using suitable brushes or smaller paint rollers adjusted to existing conditions.

The resistance of freshly painted surfaces to damage from precipitation water (washing off the paint coating) is achieved under normal conditions ( $T = 20\text{ }^{\circ}\text{C}$ , relative air humidity = 65%) within 24 hours at the latest.

Thoroughly clean the tools with water immediately after use.

## 8. Maintenance and Restoration of Painted Surfaces

Painted façade surfaces do not require any special maintenance. The non-adhering dust and other non-adhering filth can be swept, vacuumed or washed away by water. Adhering dust and more obstinate stains can be removed by light rubbing with a wet cloth or sponge soaked into a solution of usual universal household preparations and washed away by clean water.

Restore paint on surfaces, which cannot be cleaned of filth and stains in the above described manner. Restoration painting should include a new two-layer paint application as described in the chapter entitled "Paint application". Always apply adequate primer. It is possible to apply paint directly onto a surface only in case no more than two years have elapsed since the last painting.

## 9. Storage, Transportation Conditions and Durability

Storage and transportation at temperature  $+5^{\circ}\text{C}$  to  $+25^{\circ}\text{C}$ , protected from the direct sunlight, out of reach of children, MUST NOT FREEZE!!

Durability when stored in originally sealed and undamaged packaging: at least 18 months.

## 10. Other Information

Technical instructions are given based on our experiences and are given as a guideline for achieving optimal results. We cannot take any responsibility for the damage, caused by incorrect selection of a product, incorrect use or unprofessional work. JUB also bears no responsibility in cases where the substrate for the application of our products is prepared inadequately or with materials of inadequate quality from other manufacturers. In the case of applying our products to existing substrates of old coatings or pre-prepared substrates with materials from other manufacturers, it is obligatory to make appropriate test fields with all the intended applications of JUB products, in accordance with the technical instructions, before starting the work.

Safety measures: Follow the instructions on the safety data sheet of the product.

The colour shade may differ from the print in the colour chart or from the approved sample. However, the total colour difference  $\Delta E_{2000}$  – it is determined in accordance with the ISO 7724/1-3 and by a mathematical model CIE DE2000 – doesn't exceed 1.5 for colour shades from the JUBs colour charts or 2.5 for nuances from the NCS and RAL colour charts. If you wish to check the colour shade, dry the application of a render on a test surface correctly and check a standard of the concerned shade, which is stored in TRC JUB. Paint manufactured by other colour charts is the best possible approximation for JUB's primers and tinting agents. Therefore, in such cases the total colour difference from the desired nuance may be even higher than the value guaranteed above. Difference in colour shade, which is a result of unsuitable working conditions, of a colour preparation technique, which differs from the one in this technical sheet, failure to follow the equalization rules, application of the compound onto an unsuitably prepared, overly or not enough absorbing surface, more or less coarse surface, on wet or not dried enough surface, cannot be subject of complaint. For application to façade surfaces, we recommend paint with brightness (Y) over 25. Darker paints and paints of intensives colour tones, which can be achieved only with organic pigments, are somewhat less resistant to washing out with precipitation and more inclined to chalking in more demanding exploitation conditions. We shall not accept complaints for changes, which might occur for this reason on façade surfaces which pale faster. Therefore, one should consult our experts for each case individually regarding conditions for application of such paints and maintenance of processed surfaces. The list of colour shades, which could be controversial in this sense, is available at stores where JUMIX tinting stations are located as well as in our sales and technical information departments.

This technical sheet supplements and replaces all preceding editions. We reserve the right to change and supplement data in the future.

Denomination and date of publishing: TDS 100/26-pek, 24.03.2026