

Tehnički opis

EXTRA-TOP

Učvršćivač za industrijski pod

Opis

Pripremljeni malter sa posebnim aditivima i kvarcnim agregatom za ojačavanje površine novog industrijskog poda. Posедуje izuzetnu otpornost na abraziju i udare.

Klasifikovan je kao CT-C60-F7-AR2 prema EN 13813.

Primena

EXTRA-TOP se koristi u situacijama kada se zahteva visoka mehanička čvrstoća poda. Nanosi se na cementne podloge, kao što su beton ili cementna košuljica. Pogodan je za podove u industrijskim halama, podrumima, automehaničarskim radionicama, mašinskim halama, parking prostorima, skladištima, utovarnostovarnim rampama, itd.

Tehnički podaci

Oblik: cementni prah

Boje: siva, ochre, crveno-braon

Spec. gustina
suvog maltera: $1,60 \pm 0,20$ kg/l

EXTRA-TOP siva

Sila pritiska: $60,00 \pm 5,00$ N/mm²

Otpornost na savijanje: $8,00 \pm 2,00$ N/mm²

EXTRA-TOP ochre

Sila pritiska: $83,00 \pm 5,00$ N/mm²

Otpornost na savijanje: $9,50 \pm 1,50$ N/mm²

EXTRA-TOP crveno-braon

Sila pritiska: $83,00 \pm 5,00$ N/mm²

Otpornost na savijanje: $9,50 \pm 1,50$ N/mm²

Uputstvo za upotrebu

1. Podloga

Podloga može da bude:

- Armirani beton
- Cementna košuljica minimalne debljine 5 cm, koja se za podlogu (beton) vezuje uz pomoć vezivnog sloja izrađenog od ADIPLAST-a, DUREBOND-a ili FERROSEAL-a.

2. Nanošenje

EXTRA-TOP se nanosi suv, u dva sloja (prvi sloj oko 2/3 ukupne količine, drugi sloj ostatak, 1/3 ukupne količine) posipanjem po svežem betonu ili malteru neposredno čim počne da očvršćava.

Konačno, materijal se tretira sa specijalnom mašinom za glačanje (rotacionim gleterom).

Sa mašinom za gletovanje postiže se sabijanje prvog sloja do svežeg betona, a zatim sledi zbijanje i obrada drugog sloja.

Potrošnja

3-5 kg/m².

Pakovanje

EXTRA-TOP se isporučuje u papirnim vrećama od 25 kg.

Rok upotrebe – Skladištenje

Ukoliko se čuva u originalnom, neotvorenom pakovanju, na mestu zaštićenom od vlage i smrzavanja, rok upotrebe je 12 meseci od datuma proizvodnje.

Napomene

- Temperatura tokom primene treba da bude minimum +5°C.
- Proizvod sadrži cement i sa vodom reaguje alkalno, tako da je klasifikovan kao iritant.
- Pažljivo proučite upozorenja i uputstva ispisana na ambalaži proizvoda.

EXTRA-TOP

EXTRA-TOP SIVA


ISOMAT D.O.O. Prhovačka bb, 22310 Šimanovci, Serbia 11
EN 13813 CT-C60-F7-AR2 Cementitious screed material for use internally in buildings DoP No.: EXTRA-TOP/1642-03 Reaction to fire: A1_{fl} Release of corrosive substances: CT Water permeability: NPD Water vapor permeability: NPD Compressive strength: C60 Flexural strength: F7 Wear resistance: AR2 Sound insulation: NPD Sound absorption: NPD Thermal resistance: NPD Chemical resistance: NPD

EXTRA-TOP OCHRE & CRVENO-BRAON


ISOMAT S.A. 17th km Thessaloniki – Ag. Athanasios P.O. BOX 1043, 570 03 Ag. Athanasios, Greece 11
EN 13813 CT-C70-F7-AR2 Cementitious screed material for use internally in buildings DoP No.: EXTRA-TOP/1642-03 Reaction to fire: A1_{fl} Release of corrosive substances: CT Water permeability: NPD Water vapor permeability: NPD Compressive strength: C70 Flexural strength: F7 Wear resistance: AR2 Sound insulation: NPD Sound absorption: NPD Thermal resistance: NPD Chemical resistance: NPD

ISOMAT D.O.O.
GRAĐEVINSKA HEMIJA I MALTERI
Prhovačka bb, 22310 Šimanovci, Srbija
T +381 22 222 150 100, F +381 22 215 150 101
www.isomat.rs e-mail: info@isomat.rs